

## HPSW WICK - BURN CHART

The HPSW chart was based on our standard tests results. The results represent cycle of four hours, made with 145 fully paraffin wax refined.

S.V	Bleach Style SV	Mts/Kg	Flame Ht		Consumption Rate		Pool Diameter	
			In Inches	In Cm	Ounces/Hr	Grams/Hr	In Inches	In Cm
A3030	HP 1478 SW	2976	0,67	1,70	0,10	2,85	1,18	3,00
A3035	HP 962 SW	1938	0,79	2,00	0,11	3,20	1,38	3,50
A3040	HP 840 SW	1692	0,94	2,40	0,13	3,75	1,46	3,70
A3045	HP 774 SW	1558	1,02	2,60	0,14	3,90	1,50	3,80
A3050	HP 536 SW	1080	1,18	3,00	0,17	4,80	1,77	4,50
A3055	HP 450 SW	907	1,57	4,00	0,19	5,50	1,97	5,00
A3060	HP 385 SW	775	1,97	5,00	0,25	6,98	2,17	5,50
A3000	HP 348 SW	701	2,56	6,50	0,29	8,28	2,56	6,50
A3015	HP 272 SW	548	2,60	6,60	0,29	8,35	2,60	6,60
A3025	HP 220 SW	444	2,68	6,80	0,31	8,90	2,95	7,50

- Additional sizes and developments available on request.

