

HPVF WICK - BURN CHART

The HPNF chart was based on our standard tests results. The results represent cycle of four hours, made with 145 fully paraffin wax refined.

S.V	Style S.V	Mts/Kg	Yards/Lb	Flame Ht		Consumption Rate		Pool Diameter	
				In Inches	In Cm	Ounces/Hr	Grams/Hr	In Inches	In Cm
A2235	HP 751 VF	1512	750	0,98	2,50	0,14	3,89	1,77	4,50
A2265	HP 739 VF	1489	739	1,06	2,70	0,14	4,07	2,20	5,60
A2270	HP 728 VF	1467	728	1,44	3,66	0,16	4,50	2,20	5,60
A2240	HP 727 VF	1465	727	1,10	2,80	0,14	4,03	2,20	5,60
A2215	HP 580 VF	1169	580	1,18	3,00	0,16	4,48	2,80	7,10
A2218	HP 482 VF	971	482	1,18	3,00	0,17	4,91	2,80	7,10
A2220	HP 428 VF	863	428	1,42	3,60	0,19	5,35	3,15	8,00
A2210	HP 358 VF	722	358	1,57	4,00	0,22	6,11	3,35	8,50
A2225	HP 281 VF	566	281	1,77	4,50	0,29	8,09	4,13	10,50
A2230	HP 267 VF	538	267	2,17	5,50	0,29	8,34	4,13	10,50

- Additional sizes and developments available on request

