

HPZ WICK - BURN CHART

The HPZ chart was based on our standard tests results. The results represent cycle of four hours, made with 145 fully paraffin wax refined.

S.V	Style	Mts/Kg	Flame Ht		Consumption Rate		Pool Diameter	
			In Inches	In Cm	Ounces/Hr	Grams/Hr	In Inches	In Cm
B5025	HP 400 Z	806	1,14	2,9	0,12	3,3	2,24	5,7
B5085	HP 395 Z	796	0,91	2,3	0,09	2,53	2,09	5,3
B5020	HP 390 Z	786	0,98	2,5	0,1	2,81	2,17	5,5
B5010	HP 350 Z	704	1,18	3	0,12	3,49	2,36	6
B5030	HP 325 Z	655	1,26	3,2	0,13	3,55	2,44	6,2
B5015	HP 310 Z	625	1,34	3,4	0,13	3,63	2,52	6,4
B5040	HP 300 Z	605	1,57	4	0,16	4,52	2,8	7,1
B5035	HP 290 Z	585	1,54	3,9	0,15	4,18	2,76	7

- Additional sizes and developments available on request.

